

Kromasil 60 Å

SIL, CN, Diol and HILIC-D

High performance spherical silica for analytical to process scale liquid chromatography, manufactured to give high reproducibility and chemical stability.

Functionalized Kromasil 60 Å is manufactured using mono- or trifunctional silanes.

Product characteristics

Particle sizes

Phase	Particle size [µm]				
	5	7	10	13	16
SIL	•	•	•	•	•
CN	•		•		•
Diol	•		•		
HILIC-D	•		•		

Particle size distribution

(Coulter Multisizer)

dp [µm]	dp ₉₀ /dp ₁₀
10,13,16	≤ 1.70
7	≤ 1.60
5	≤ 1.55

Spec surface area

540 m²/g (multi-point BET)

Pore volume

1.2 ml/g (N₂-adsorption)

Pore size

80 Å (N₂-adsorption)

Pore size distribution

80% ± 15 Å (N₂-adsorption)

Coverage

(elemental analysis)

CN	12% C, 2.3% N	3.8 µmol/m ²
Diol	10% C	3.5 µmol/m ²
HILIC-D	10% C	3.5 µmol/m ²

Chemical purity

Typical figures (AAS or ICP):

Na:	< 10 ppm
Al:	< 5 ppm
Fe:	< 5 ppm

Mechanical stability

Allows repeated packing at up to 700 bar (10 000 psi).

Packed density

SIL:	0.45 g/ml
CN:	0.52 g/ml
Diol:	0.53 g/ml
HILIC-D:	0.53 g/ml

Delivery

Kromasil bulk is delivered in polyethylene bottles or in polyethylene bags packed in plastic drums.

Kromasil, patented by Nouryon, is manufactured in multi-kilogram batches with high reproducibility.

The management system for the development, production and marketing of Kromasil is ISO 9001 certified.

The Kromasil production site is ISO 14 001 certified.